

## AMENDMENTS TO THE CLAIMS

1. (currently amended) A masterbatch ~~composition~~composition comprising (percent by weight):

A) 50%-90% of a crystalline polypropylene component comprising:

A<sup>I</sup>) from 25% to 75% of a fraction having a melt flow rate MFR<sup>I</sup> of from 0.1 to 10 g/10 min.;~~and~~min.; and

A<sup>II</sup>) from 25% to 75% of a fraction having a melt flow rate value MFR<sup>II</sup> ~~equal to or lower~~no greater than 100 g/10 min.;

wherein ~~the~~ ratio MFR<sup>I</sup>/MFR<sup>II</sup> is from 5 to 60, and the fractions (A<sup>I</sup>)A<sup>I</sup> and (A<sup>II</sup>)A<sup>II</sup> are independently selected from the group consisting of a propylene homopolymer, a random copolymer of propylene containing up to 3% of ethylene, and a random copolymer of propylene containing up to 6% of at least one C4-C10  $\alpha$ -olefin; and

B) 10%-50% of a copolymer component ~~of~~comprising ethylene and at least one C<sub>3</sub>-C<sub>10</sub>  $\alpha$ -olefin, the copolymer containing from 15% to 50% of ethylene, and optionally minor amounts of a diene;

said masterbatch composition having an MFR and a value of the intrinsic viscosity  $[\eta]$  of ~~the~~ fraction soluble in xylene at room temperature (about 25 °C) ~~equal to or higher than~~of at least 3.5 dl/g.

2. (currently amended) The masterbatch composition of claim 1, ~~having a MFR value of from~~ wherein the MFR is 0.1 to 10 g/10 min.

3. (currently amended) A thermoplastic polyolefin composition ~~containing the~~comprising a masterbatch composition and at least one olefin polymer different from the masterbatch composition, the masterbatch composition comprising (percent by weight):~~of claim 1~~

A) 50%-90% of a crystalline polypropylene component comprising:

A<sup>I</sup>) from 25% to 75% of a fraction having a melt flow rate MFR<sup>I</sup> of from 0.1 to 10 g/10 min.; and

A<sup>II</sup>) from 25% to 75% of a fraction having a melt flow rate value MFR<sup>II</sup> no greater than 100 g/10 min.;

wherein a ratio  $MFR^I/MFR^{II}$  is from 5 to 60, and the fractions  $A^I$  and  $A^{II}$  are independently selected from the group consisting of a propylene homopolymer, a random copolymer of propylene containing up to 3% of ethylene, and a random copolymer of propylene containing up to 6% of at least one C<sub>4</sub>-C<sub>10</sub>  $\alpha$ -olefin; and

B) 10%-50% of a copolymer component comprising ethylene and at least one C<sub>3</sub>-C<sub>10</sub>  $\alpha$ -olefin, the copolymer containing from 15% to 50% of ethylene, and optionally minor amounts of a diene;

said masterbatch composition having an MFR and a value of the intrinsic viscosity  $[\eta]$  of a fraction soluble in xylene at room temperature (about 25 °C) at least 3.5 dl/g.

4. (currently amended) The thermoplastic polyolefin composition of claim 3, wherein the ~~content of masterbatch composition is~~ present in an amount from 5% to 20% by weight with respect to the total weight of the thermoplastic composition.
5. (currently amended) The thermoplastic polyolefin composition of claim 3, wherein the olefin polymers other than those contained in the masterbatch composition are selected from the group ~~existing~~ consisting of:
  - 1) crystalline propylene homopolymers;
  - 2) crystalline copolymers of propylene with at least one of ethylene ~~and/or~~ and a C<sub>4</sub>-C<sub>10</sub>  $\alpha$ -olefin, wherein the total comonomer content ranges from 0.05 to 20% by weight with respect to the weight of the copolymer;
  - 3) crystalline ethylene homopolymers and copolymers with at least one of propylene ~~and/or~~ and C<sub>4</sub>-C<sub>10</sub>  $\alpha$ -olefins;
  - 4) elastomeric copolymers of ethylene with at least one of propylene ~~and/or~~ and a C<sub>4</sub>-C<sub>10</sub>  $\alpha$ -olefin, optionally containing minor quantities of a diene;
  - 5) a thermoplastic elastomeric composition comprising ~~one or more~~ at least one of propylene homopolymers ~~and/or~~ and the copolymers of item 2) and an elastomeric moiety comprising ~~one or more~~ at least one of the copolymers of item 4), containing the ~~said elastomeric moiety~~ in quantities from 5 to 80% by weight; and
  - 6) blends of ~~two or more~~ at least two of the polymers or compositions of items 1) to 5).
6. (currently amended) A process for preparing ~~the~~ a masterbatch composition comprising (percent by weight):

A) 50%-90% of a crystalline polypropylene component comprising:

A<sup>I</sup>) from 25% to 75% of a fraction having a melt flow rate MFR<sup>I</sup> of from 0.1 to 10 g/10 min.; and

A<sup>II</sup>) from 25% to 75% of a fraction having a melt flow rate value MFR<sup>II</sup> no greater than than 100 g/10 min.;

wherein a ratio MFR<sup>I</sup>/MFR<sup>II</sup> is from 5 to 60, and the fractions A<sup>I</sup>) and A<sup>II</sup>) are independently selected from the group consisting of a propylene homopolymer, a random copolymer of propylene containing up to 3% of ethylene, and a random copolymer of propylene containing up to 6% of at least one C4-C10  $\alpha$ -olefin; and

B) 10%-50% of a copolymer component comprising ethylene and at least one C<sub>3</sub>-C<sub>10</sub>  $\alpha$ -olefin, the copolymer containing from 15% to 50% of ethylene, and optionally minor amounts of a diene;

said masterbatch composition having an MFR and a value of the intrinsic viscosity  $[\eta]$  of a fraction soluble in xylene at room temperature (about 25 °C) of at least 3.5 dl/g;

the process comprising polymerizing at least one monomer in-of-claim 1 by a sequential polymerization, comprising at least three sequential steps, wherein components (A) and (B) are prepared in separate subsequent steps, operating in each step, except the first step, in the presence of the polymer formed and the catalyst used in the preceding step.

7. (currently amended) Bumpers and fascia comprising ~~thea~~ masterbatch composition ~~of-claim 1-comprising~~ (percent by weight):

A) 50%-90% of a crystalline polypropylene component comprising:

A<sup>I</sup>) from 25% to 75% of a fraction having a melt flow rate MFR<sup>I</sup> of from 0.1 to 10 g/10 min.; and

A<sup>II</sup>) from 25% to 75% of a fraction having a melt flow rate value MFR<sup>II</sup> no greater than than 100 g/10 min.;

wherein a ratio MFR<sup>I</sup>/MFR<sup>II</sup> is from 5 to 60, and the fractions A<sup>I</sup>) and A<sup>II</sup>) are independently selected from the group consisting of a propylene homopolymer, a random copolymer of propylene containing up to 3% of ethylene, and a random copolymer of propylene containing up to 6% of at least one C4-C10  $\alpha$ -olefin; and

B) 10%-50% of a copolymer component comprising ethylene and at least one C<sub>3</sub>-C<sub>10</sub>  $\alpha$ -olefin, the copolymer containing from 15% to 50% of ethylene, and optionally minor amounts of a diene;

said masterbatch composition having an MFR and a value of the intrinsic viscosity  $[\eta]$  of a fraction soluble in xylene at room temperature (about 25 °C) of at least 3.5 dl/g.